


Interpore 2018, New Orleans, May 14-17, 2018

Christopher Kühnle, Mehdi Azimian, Liping Cheng, Sven Linden, Andreas Wiegmann

#### MATH2MARKET OVERVIEW





#### **Location and Contact**







# **GeoDict for Filtration: Liquid Filtration Portfolio**











| Filter Media   |   | Clean Filter<br>Parameters  |   | Liquid Filtration<br>Experiments     | Li | iquid Filtration Results  |
|--|---|---|---|--------------------------------------|----|---|
| <br>Nonwoven fabrics Woven fabrics Foams Membranes Metal wire meshes Pleats & support meshes | : | Media thickness Fiber diameters Fiber orientation Grammage Pore size distribution Bubble point Percolation path | : | Multi pass tests Standard test dusts |    | Initial pressure drop Pressure drop evolution Initial filter efficiency Fractional efficiencies Filter capacity Filter class Filter clogging behavior |
|  |   |   |   |                                      |    |   |

### Filter Media Design



**Filter** 

Efficiency

Dust holding capacity (DHC), pressure drop, and filter efficiency describe the performance of a filter
 They influence each other and it is hard to improve all of them at the same time
 These parameters depend mainly on the porous microstructure (e.g. pore size distribution)


**Pressure** 

Drop  $\Delta P$ 

■ In this presentation we want to optimize the DHC while keeping initial pressure drop and clean filter efficiency the same

### Simulate filtration at different scales






### Filter life-time simulations





## Modeling of coarse/fine mixed media filter





#### Thick fibers (blue):

Diameter: 20 µm

Orientation: Anisotropic 8/1

Material: Glass Vol. ratio: 60%

#### Thin fibers (Yellow):

Diameter: 4 µm

Orientation: Anisotropic 8/1


Material: Glass Vol. ratio: 40%

$$\beta_d = \frac{n_{\geq d, Upstream}}{n_{\geq d, Downstream}}$$


## Modeling of three filter media structures




Homogeneous



Linear




Exponential



## Homogeneous medium






Domain 600x600x1600 μm


#### Linear medium





Flow direction






Domain 600x600x1600 μm


## **Exponential medium**





Flow direction





Domain 600x600x1600 μm

# Structural comparison



| Structure  | Homogeneous          | Linear                            | Exponential                        |
|--|----------------------|-----------------------------------|------------------------------------|
| Size [μm]  | 600x600x1600         | 600x600x1600                      | 600x600x1600                       |
| Distribution of coarse fiber / fine fiber                | Uniform /<br>Uniform | Uniform /<br>Linear(1,2,3,4,5,6,) | Uniform / Exponential(1,2,4,8,16,) |
| Permeability [m²]  | 5.47E-11             | 5.48E-11                          | 5.53E-11                           |
| $oldsymbol{eta_{22\mu m}}$                               | 200                  | 200                               | 200                                |
| Object solid volume percentage in domain (porosity in %) | 6.11<br>(93.89 %)    | 5.9<br>(94.1 %)                   | 5.43<br>(94.57 %)                  |
| Volume coarse fiber / Volume<br>fine fiber               | 60/40                | 60/40                             | 60/40                              |

## **Experimental setup**



Used Fluid: Oil


Temperature: 20 °C

Used Particles: ISO Fine A2 test dust


Particle Density: 2560 kg/m<sup>3</sup>

Particle Collision Model: Sieving

Flow regime: Laminar




Multi-pass filter test schematic based on ISO 4548-12




# Transient filtration simulation (Homogeneous structure)






# Transient filtration simulation (Homogeneous structure)





# Animation of the filtration simulation (Linear structure)







# Comparison of particle depositions




Homogeneous



Linear




**Exponential** 



# Multipass simulation results: Pressure-drop over time






> The exponentially increasing media shows the lowest pressure-drop increase through the life-time simulations.

# Multipass simulation results: Pressure-drop over total deposited dust





> The exponentially increasing media shows the lowest pressure-drop increase & the highest DHC through the life-time simulations.

#### **Conclusions**



- ✓ The simulations of filter and filtration can be done in different scales.
- ✓ By modification of the micro-structure of filter media, the macroscopic properties can be optimized.
- ✓ The gradient distribution of fibers through the media thickness, can improve the filtration characteristics.
- ✓ The exponential media shows the lowest pressure-drop increase & the highest DHC through the life-time simulations.
- ✓ The computer simulation helps to find the best performed filter media without being physically produced.

### Thank you for your attention.



#### Visit us at our Booth #8 in Hall I-1

